

Technical datasheet

## Agrolys WH130 L25

**Agrotextiles - PP Woven groundcovers** 

**Technical Textiles** 

## **Functions**

Stimulates the growth of the plants which need a high reflection of light Prevents the growth of weeds Not harmful to the environment and prevents the use of herbicides

## **Product Specifications**

PROPERTIES	TEST METHOD	VALUE		UNIT	TOLERANCE
		WARP	WEFT		
MATERIAL		PP	PP		
TISSUE COLOUR		white			
PATTERN		line every 9.8 in			
		line every 25 cm			
COLOUR LINING		blue			
TISSUE WEIGHT	ASTM D5261	3.83		oz/y²	± 5 %
		130		g/m²	± 5 %
WIDTH		10.83 - 13.62 - 16.88 330 - 415 - 515		ft	± 0.1 ft
				cm	± 2 cm
LENGTH		328 100		ft	± 2 %
				m	± 2 %

## **Technical characteristics**

PROPERTIES	TEST METHOD	VALUE		UNIT	TOLERANCE
		WARP	WEFT		
TRAPEZOÏD TEAR STRENGTH	ASTM D4533	90	112	lbs	± 20 %
		0.40	0.50	kN	± 20 %
GRAB TENSILE STRENGTH	ASTM D4632	180	180	lbs	± 20 %
		0.80	0.80	kN	± 20 %
GRAB ELONGATION	ASTM D4632	30.0	25.0	%	± 20 %
SHRINKAGE	15' à 70 °C	1.0	1.0	%	MAX
MULLEN BURST	ASTM D3786	282		psi	± 20 %
		1944		kPa	± 20 %

This information contained in this document is based on testing carried out by our laboratory or external research institutes and literature data, and based on Mean Values. This TDS is valid until further notice. To the best of our knowledge and at the time of publication, this information is true and accurate. It shall however, in no event be held to constitute or imply warranty undertaking express or implied commitment from the part of Beaulieu International Group – Division Beaulieu Technical Textiles. No liability whatever can be accepted by Beaulieu International Group – Division Beaulieu Technical Textiles with regard to the handling, processing or use of the product concerned which must in all cases be used in accordance with all applicable laws and regulations. The mentioned characteristics are not valid when the fabric has been in contact with sulphur-, chlorine-, iron- and brominederivates, as well as with copper sulphates and if the product is not installed and used in strict accordance with the installation instructions.