Technical datasheet

# Agrolys GR90 L15

Agrotextiles - PP Woven groundcovers



# **Technical Textiles**

#### Functions

Stimulates the growth of the plants Prevents the growth of weeds Not harmful to the environment and prevents the use of herbicides

### **Product Specifications**

PROPERTIES	TEST METHOD	VALUE		UNIT	TOLERANCE
		WARP	WEFT		
MATERIAL		PP	PP		
TISSUE COLOUR		green			
PATTERN		line 15 cm			
COLOUR LINING		green			
TISSUE WEIGHT	ISO 3801	90		g/m²	± 5 %
WIDTH		150 - 420		cm	± 2 cm
LENGTH		100		m	± 2 %

## **Technical characteristics**

PROPERTIES	TEST METHOD	VALUE		UNIT	TOLERANCE		
		WARP	WEFT				
BREAK ELONGATION	ISO 13934-1	18	17	%	± 20 %		
TENSILE STRENGTH	ISO 13934-1	850	700	N/5cm	± 20 %		
PERFORATION RESISTANCE	EN ISO 13433	20		mm	MAX		
UV-STABILIZATION	ISO 4892-3 cycle 3	≅ 400 kLy					
SHRINKAGE	15' à 70°C	1,0	1,0	%	MAX		
WATERPERMEABILITY	ISO 11058	0,010		m/s	± 50 %		
LIGHT TRANSMISSION	NF G 07-162	<1		%			
REMARKS	UV-Stabilization : Based on QUV testing min 37000 h (cycles of 5 h light exposure UV-A 340 nm 0,83 W/m <sup>2</sup> at 50°C and 1 h water spray), which corresponds theoretically to a solar irradiation of 400 kLY. In a climate zone of 90 kLy/y (Western Europe) this corresponds to 4-5 years.						

This information contained in this document is based on testing carried out by our laboratory or external research institutes and literature data, and based on Mean Values. This TDS is valid until further notice. To the best of our knowledge and at the time of publication, this information is true and accurate. It shall however, in no event be held to constitute or imply warranty undertaking express or implied commitment from the part of Beaulieu International Group – Division Beaulieu Technical Textiles. No liability whatever can be accepted by Beaulieu International Group – Division Beaulieu Technical Textiles with regard to the handling, processing or use of the product concerned which must in all cases be used in accordance with all applicable laws and regulations. The mentioned characteristics are not valid when the fabric has been in contact with sulphur-, chlorine-, iron- and brominederivates, as well as with copper sulphates and if the product is not installed and used in strict accordance with the installation instructions.